

EUROPEAN COMMISSION

HORIZON 2020 PROGRAMME - TOPIC H2020-LC-BAT-2020
Sodium-Ion and sodium Metal BAtteries for efficient and sustainable
next-generation energy storage

GRANT AGREEMENT No. 963542



SIMBA – Deliverable Report

<< D2.6 – Round robin test with developed electrodes,
electrolyte and cell process showing stability > 300
cycles >>

Deliverable No.	SIMBA D2.6	
Related WP	WP2	
Deliverable Title	Round robin test with developed electrodes, electrolyte and cell process showing stability >300 cycle	
Deliverable Date	2023-06-30	
Deliverable Type	REPORT	
Dissemination level	Confidential – member only (CO)	
Written By	Maidar Zarrabeitia (KIT)	2023-06-09
Checked by	Piter Miedema (UNR)	2023-06-26
Reviewed by (if applicable)	Tengfei Song (UBham), Waleri Milde (FHG-ISE)	2023-06-19
Approved by	Ralf Riedel (TUDa)	2023-06-26
Status	Final	2023-06-26



This project has received funding from the European Union's Horizon 2020 research and innovation programme under grant agreement No 963542.

Publishable summary

SIMBA aims to develop a highly cost-effective, safe, and all-solid-state sodium-ion battery using single-ion polymer as an electrolyte for large-scale stationary applications. Single-ion polymer electrolytes (SIPes) are novel solid-state electrolytes where the anion is bonded covalently to the polymer backbone, and the cation is the only mobile species. Therefore, the anion polarization is avoided, improving the sodium ion transference number close to one and enhancing the electrochemical stability window and ionic conductivity at room temperature.

D2.6 is the last deliverable associated with Work Package 2 (WP2: Lab scale material and process development) and allows us to achieve milestone two (MS02: The laboratory cell fabricated from optimized materials meets the performance target). The activities summarized in D2.6 consists of manufacturing all-solid-state polymer-based sodium-ion batteries at lab-scale with the selected electroactive materials in M23, such as Prussian white (PW) from Altris as a cathode, sawdust-derived hard carbon (sd-HC) from IFE and upscale by Elkem as an anode and sodium polysiloxane (Na-PSiO) from KIT as a SIPE with cycling stability of > 300 cycles (see MS01: Selection of the electroactive materials and the corresponding deliverables D2.1¹-D2.5² submitted in M20-M23³⁻⁵).

The cycling stability of both studied SIPes (3D networking Na[STFSI]:PETMP:PET4A:PVDF-HFP and Na-PSiO, see D2.5 for more details)² was investigated first in Na|SIPE|Na symmetric cells, exhibiting excellent compatibility against Na metal with a cycling stability of > 300 cycles. Later, half- and full-cells were studied by incorporating the polymer electrolyte into the cathode and anode electrodes (more details in D4.4)⁶. The PW|SIPE|Na metal all-solid-state sodium half cells deliver similar and stable capacities as in liquid baseline cells when low current densities are applied. However, their performance at high current densities should be improved. The sd-HC:Na-PSiO|Na-PSiO|Na metal all-solid-state sodium half cells deliver lower specific capacity than liquid electrolytes upon cycling. However, they achieved the target of D2.6, stability of more than 300 cycles.

The all-solid-state sodium full cells are still under optimization. A huge capacity decay is observed in the initial cycles by increasing the current density, probably due to the high polarization, hindering the determination of the proper N/P ratio. Incorporation of polymer electrolyte into the cell is challenging, and moving from liquid to polymer electrolyte cells is not straightforward. Indeed, a few reported full cells using sodium-based polymer electrolytes could be found in the literature due to the system's difficulty. Nevertheless, the all-solid-state sodium cells show acceptable cycling stability within the target; however, the delivered specific capacity should be enhanced upon cycling, mainly at relatively high current densities.

8 Appendix B- Acknowledgement

The author(s) would like to thank the partners in the project for their valuable comments on previous drafts and for performing the review.

Project partners:

#	Partner	Partner Full Name
1	TUDa	TECHNISCHE UNIVERSITAT DARMSTADT
2	UU	UPPSALA UNIVERSITET
3	UBham	THE UNIVERSITY OF BIRMINGHAM
4	WMG	THE UNIVERSITY OF WARWICK
5	KIT	KARLSRUHER INSTITUT FUER TECHNOLOGIE
6	CEA	COMMISSARIAT A L ENERGIE ATOMIQUE ET AUX ENERGIES ALTERNATIVES
7	IFE	INSTITUTT FOR ENERGITEKNIKK
8	SAS	USTAV ANORGANICKEJ CHEMIE SLOVENSKA AKADEMIA VIED (Institute of Inorganic Chemistry, Slovak Academy of Sciences)
9	FHG	FRAUNHOFER GESELLSCHAFT ZUR FOERDERUNG DER ANGEWANDTEN FORSCHUNG E.V.
10	Elkem	ELKEM AS
11	YUN	YUNASKO-UKRAINE LLC
12	SAFT	SAFT
13	Altris	ALTRIS AB
14	Recupyl	TES RECUPYL SAS
15	UNR	UNIRESEARCH BV

Appendix D – Disclaimer/Acknowledgement



Copyright ©, all rights reserved. This document or any part thereof may not be made public or disclosed, copied or otherwise reproduced or used in any form or by any means, without prior permission in writing from the SIMBA Consortium. Neither the SIMBA Consortium nor any of its members, their officers, employees or agents shall be liable or responsible, in negligence or otherwise, for any loss, damage or expense whatever sustained by any person as a result of the use, in any manner or form, of any knowledge, information or data contained in this document, or due to any inaccuracy, omission or error therein contained.

All Intellectual Property Rights, know-how and information provided by and/or arising from this document, such as designs, documentation, as well as preparatory material in that regard, is and shall remain the exclusive property of the SIMBA Consortium and any of its members or its licensors. Nothing contained in this document shall give, or shall be construed as giving, any right, title, ownership, interest, license or any other right in or to any IP, know-how and information.

This project has received funding from the European Union's Horizon 2020 research and innovation programme under grant agreement No 963542. The information and views set out in this publication does not necessarily reflect the official opinion of the European Commission. Neither the European Union institutions and bodies nor any person acting on their behalf, may be held responsible for the use which may be made of the information contained therein.